

SUPERTUF ROPE SPECIFICATIONS 3 STRAND

PP SUPERTUF CONFIRMS TO IS 14929.2001

Diameter		Circumference	Runnage Mtrs. Coil	Weight (220 Mtrs Coil)	Weight (500 Mtrs Coil)	Minimum Breaking Strength
mm	Inch	Inch	Mtrs/Kg	Kgs	Kgs	Kgf
4	5/32	1/2	135.00	1.63	3.70	305
6	1/4	3/4	60.00	3.67	8.34	675
8	5/16	1	33.30	6.60	15.00	1215
10	3/8	1.1/8	22.00	10.00	22.70	1845
12	1/2	1.1/2	15.20	14.50	33.00	2700
14	9/16	1.3/4	11.00	20.00	45.40	3690
16	5/8	2	8.60	25.50	58.00	4320
18	3/4	2.1/4	6.80	32.50	73.90	5490
20	13/16	2.1/2	5.50	40.00	90.90	6840
22	7/8	2.3/4	4.50	48.50	110.20	8370
24	1	3	3.90	57.00	128.20	9450
28	1.1/8	3.1/2	2.80	78.00	177.50	13050
32	1.5/16	4	2.20	101.00	230.00	16650

Tolerance:

4 mm to 8 mm	+/-10%
10 mm to 14 mm	+/-8%
16 mm and above	+/-5%